

# Analytical Testing Service Laboratories, Inc.

P.O. Box 1118, Joplin, Missouri 64802

(417) 782-6573

Ash Grove Resources, LLC  
5375 SW 7th Street, Suite 400  
Topeka, KS 66606-2552  
1-800-643-7608

January 21, 2010

Attn: Brady E. Pryor

Re: 9707- Jeffrey Fly Ash Sample 2000 Ton Composite Unit 1 - 12/2-11/09

	ASTM C-618 Class "C" <u>Requirements</u>	<u>Actual</u>
Fineness (+325 Mesh)	34% Max	14.00%
Fineness Variation	5% Max	0.90%
Moisture Content	3% Max	0.08%
Specific Gravity	****	2.78
Specific Gravity Variation	5% Max	0.30%
Loss on Ignition	6% Max	0.24%
Soundness	0.8% Max	0.07%
S.A.I., 7 Days	75% Min	100.80%
S.A.I., 28 Days	75% Min	103.00%
Water Req. % Control	105% Max	93.40%
Silica SiO <sub>2</sub>	****	30.07%
Aluminum Oxide Al <sub>2</sub> O <sub>3</sub>	****	21.05%
Ferric Oxide Fe <sub>2</sub> O <sub>3</sub>	****	6.15%
Total	50% Min	57.27%
Sulfur Trioxide SO <sub>3</sub>	5% Max	1.98%
Calcium Oxide CaO	****	28.46%
Magnesium Oxide MgO	****	6.77%

We certify the above was tested in accordance with ASTM C-618.

Analytical Testing Service Laboratories, Inc.



John K. Cupp, Manager